

POWDER FLUX 1232

INDUCTION BRAZING OF STAINLESS STEEL WITH ALUMINIUM ALLOYS SILICON CLADED

1 ➤ PRODUCT DESCRIPTION.

The Flux 1232 has a high pickling power. It is especially recommended for bonding pieces of aluminium or stainless steel on aluminium cladded aluminium/silicon.

2 ➤ CHARACTERISTICS - PHYSICO-CHEMICAL PROPERTIES, COMPOUND ELEMENTS.

White powder with restrictive particles size range.

3 ➤ PRODUCT APPLICATIONS.

Induction brazing of stainless steel or aluminium pieces on aluminium cladded silicon pieces.

4 ➤ DIRECTIONS FOR USE.

For induction or torch brazing between 530 and 660°C. No corrosive residues. The parts remain inert.

Before brazing, the parts must be correctly prepared and cleaned. The flux can be used dry or mixed with clean water to obtain a homogenous paste.

Apply carefully the flux and the filler metal on the brazing area, place the aluminium disk and braze by induction.

5 ➤ USING CARE AND RECOMMENDATIONS

In order to keep the proper reactivity of the flux, avoid overheating it.

No particular risk.

For all other information, please see the Material Safety Data Sheet also available on our web site (www.stts-flux.com) or contact us directly.

